

TECHNICAL DATA SHEET (TDS)

Class Sentetik

DESCRIPTION: Alkyd resin based, glossy paint for topcoat applications.

CHARACTERISTIC: -High adhesiveness and covering ability. -Easily appliable. -Resistant against physical and chemical effects. -Easy cleanable -Flexible.

APPLICATION SURFACES: Can be applied on exterior and interior wooden, plaster, metal amd similar surfaces.

TECHNICAL INFORMATION:

Structure: Alkyd resin based, synthetic and glossy.

Consumption: 14-18 (m²/lt), 70-85 (g/m²)

Thinning Ratio: % 10-15.

Recommended Primer: Silkcoat Synthetic Primer, Silkcoat Lüxe Synthetic Primer.

Recommended anti-rust and polish: Silkcoat Anti-rust and Silkcoat Pinoten on wooden surfaces.

Application tools: Brush, roller, spray gun

Drying: Touch dry :after 1 – 2 hours ; dust repulsive; after 2 – 3 hours; hard dry; after 10 – 12 hours .Leave

minimum 12 hours between coats.

Viscosity: 100 KU ± 10 (23 ° C)

Density: $1,09 \pm 0,10(g/ml)$

Amount of solid: $(62 \pm 2)\%$

Brilliance: (60º Minumum 80 Gloss)

Thickness of dry coat: 25 ± 5 micron

Thickness of wet coat: 60 ± 5 micron



TECHNICAL DATA SHEET (TDS)

SURFACE PREPARATION: Silkcoat Synthetic Primer is applied to the surfaces which have been puttied. Silkcoat Universal Primer is applied to surfaces prepared with satin plaster. On the wooden floors, the knots on the surfaces are burned and after being filled with Silkcoat Pinoten, Silkcoat Synthetic Primer is applied. After metal, oil, dirt and rust are cleaned thoroughly, antirust should be applied. Synthetic paint can be applied after preparation. Wait 12 hours between coats. For brush and roller application, the paint should be thinned with 5-10% of synthetic tin.

CAUTION:

R10 Flammable.

R51 / 53 Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

R65 Harmful: may cause lung damage if swallowed.

R66 Repeated exposure may cause skin dryness or cracking.

R67 Vapors may cause drowsiness and dizziness.

S2 Keep out of reach of children.

S16 Keep away from sources of ignition – No smoking.

S24 / 25 Avoid contact with eyes and skin.

S37 Wear suitable gloves.

S51 Use only in well-ventilated areas.

S57 Use a suitable container to avoid contamination.

S60 Dispose of this material and its container as hazardous waste.

S61 Avoid release to the environment. Refer to Special Instructions for Use / Safety Data Sheet.

S62 If swallowed, do not induce vomiting. Contact the first aid service immediately and show the container or label.

STORAGE: Keep at a cool and clean place away from sun light. It can be stored unopened 1 year at room temperature.

PACKAGING: 12 lt, 2,2 lt, 0.75 lt tin Bucket.



TECHNICAL DATA SHEET (TDS)

