

Elasticoat

ING- DESCRIPTION: Pure acrylic binder based matt appearance elastic exterior paint.

CHARACTERISTIC: Elasticoat Paint, which has superior flexibility, does not crack due to its elastomer property. It is resistant to sun rays (UV), rain, snow and industrial effects. It is easy to apply and has excellent closure and adhesion properties.

APPLICATION SURFACES: The floor preparation can be applied to all clean and dry exterior surfaces.

TECHNICAL INFORMATION:

Structure: Pure acrylic

Consumption: Single coat: 6- 10 (m²/lt), 100-170 (g/m²)

Thinner: Water

Thinning Ratio: % 10 -15 water

Density: 1,58 ± 0,05 (g / ml)

Drying: Touch dry: after 15-20 min, Dust repulsive: after 1 hour, Hard dry: after 24 hours

Viscosity: 120 KU ± 10 (23 ° C)

PH: 8 – 9

APPLICATION: The application surface should be free from all kinds of dust, rust, dirt, oil and old paint residues. After cleaving the surface cracks with Silkcoat External Putty and smoothing, apply Silkcoat Acrylic Primer to obtain a clean, dry and solid surface. Elasticoat Paint is applied in 2 layers by roller, brush or spray method by thinning with 20-30% of the first layer and 10-15% of the second layer with clean water. Wait at least 2 hours between coats depending on the air temperature. Tools should be cleaned immediately after application. For new coated surfaces, at least 28 days must be waited for the application of paint to the surface. The paint should be mixed until it is completely homogenous before use. Ambient and surface temperature should be between + 5°C and + 35°C during application and product drying. If applied on very bright and glassy surfaces, a solid surface should be formed by smoothing the surface first to ensure better adhesion.

CAUTION: -Avoid getting eye and skin contact. In case wash with plenty of water. -Preserve in a tightly closed container. -Keep above the reach of children -Do not dump into sewer system.

STORAGE: Keep at a cool and clean place away from sun light. It can be stored unopened 1 year at room temperature.

PACKAGING: 15 lt, , 2,5 lt PE Bucket

Poz No: Y.25.004/04, Y.25.004/09