

## SX 2005

**Product Description:** Pure acrylic binder based, surface protection polish for Silkcoat Mineral Plaster.

### Features:

SX 2005 POLISH, produced specifically for mineral plaster, provides excellent water resistance thanks to the film layer it creates. Mineral plaster and other exterior surfaces applied give vitality of the decorative side, as well as increase the resistance of mineral plaster to the surface and enable it to be used for many years. It penetrates into the plaster surface and sticks in a very strong way. Due to its water-based structure, it does not harm human health and environment.

### Application surfaces:

On mineral Plaster and exterior surfaces, SX 2005 is applied in double layer.

### Technical Data:

Structure: Pure Acrylic

Consumption: 6-10 (m<sup>2</sup> / lt), 120-180 (g / m<sup>2</sup>)

Density: 1.03 ± 0.02 (g / ml)

Thinning ratio: 40-50%

**Application tools:** Roller or Sprayer Drying: Drying 4 – 8 hours; Hardening for application of topcoats 24 hours.

**Density:** 1,00 +/- 0,05

**Application:**

The surface to be applied must be clean, dry and stable surface by removing all kinds of dust, dirt and oil. If necessary, the surface defects and cracks should be repaired with Silkcoat Putty. Silkcoat SX 2005 is diluted with 10-15% of clean water and applied as a single layer by roller or brush. Tools should be cleaned with water after application. The ambient and surface temperature should be between + 5°C and + 35°C during application and during the full drying time of 24 hours.

**Warning:**

S2: Keep out of the reach of children.

S24 / 25: Avoid contact with eyes and skin.

S46: If swallowed, seek medical advice immediately; Show the container or label.

Store the product in a tightly closed container.

Do not pour into the sewer.

Brilliance point: 41 °C. flammable, harmful when swallowed and breathed.

**Storage:**

Storage life is at least 1 year in room conditions.

**Package:**

15 lt, 5 lt, 2,5 lt PE bucket.